

Solar Screen

GOLD 80 C

Solar Control
Coloured - Interior

Description

Gold 80 C films are highly effective at reducing solar heat gain, whilst at the same time continuing to allow most natural light to pass through. They help noticeably reduce solar glare, conveying a touch of colour and customization to the external aspect of a building.

Certified B Corporation

Visible Light Transmission (%)



Visible Light Reflection - External (%)



UV Rejection (%)



Total Solar Energy Rejected (%)



Solar Screen

GOLD 80 C

Solar Control
Coloured - Interior

Characteristics

Warranty
Up to 10 years

Fire Resistance Rating
M1

Storage in recommended conditions
3 years

REACH / RoHS
Compliant

Widths Available
152 cm

Installation Type
Interior

Color From the Outside
Gold

Length
30.5 m

Product Carbon Footprint (LCA)
1.56 kgCO2e/m²

Construction

1 Scratch-resistant hard coating providing surface protection, durability, and ease of cleaning
2 High optical quality polyester, with an IR-blocking metallic particle coating
3 Bonding adhesive
4 High optical quality dyed polyester
5 PS adhesive, polymerizes with glass within 15 days
6 Protection PET release liner, disposable after installation

Composition
PET

Thickness
50 µm

Details



Energy and environmental benefits[01]

Energy savings
N/A

Carbon footprint reduction
N/A

Financial savings
N/A

Access our energy savings calculator

Optical and solar properties

	Single 3mm		Double Low-E	
Pane type	No film	With Film	No film	With Film
UV Rejection (%)	25	99	40	N/A
Visible Light Transmission (%)	**91**	**15**	**82**	**N/A**
Visible Light Reflection - External (%)	8	50	11	N/A
Visible Light Reflection - Internal (%)	8	63	12	N/A
Solar Energy Reflection (%)	5	50	28	N/A
Solar Energy Absorption (%)	8	38	12	N/A
Solar Energy Transmission (%)	87	12	60	N/A
Total Solar Energy Rejected (%)	**12**	**78**	**35**	**N/A**
Glare Reduction (%)	-	84	-	N/A
Shading Coefficient	-	0.25	-	N/A
g-value	**0.88**	**0.22**	**0.65**	**N/A**
U-value (W/m².°C)	5.8	5.6	1.1	N/A

Application advice[02]

Vertical situation and for a standard glazed surface

Clear Single Pane	✓
Tinted Single Pane	✓
Reflective Tinted Single Pane	✓
Clear Double Pane	!
Tinted Double Pane	×
Reflective Tinted Double Pane	✓
Gas-Filled Double Pane - Low E	×
Stadip Ext. Clear Double Pane	!
Stadip Int. Clear Double Pane	×

✓ Yes × Not recommended ! Caution

Installation and Maintenance Advise

Use Slide On (600-FO2) or Film On (600-F0355) diluted at 2 cL/L of water for installation and cleaning. Do not clean for one month after installation or apply stickers/adhesives on the film.

Access the installation and maintenance advice video

01 Values based on a study carried out on an air-conditioned building located in Luxembourg, with a film applied on a low-E double glazing, facing East. The heating months considered are from October to March, and the cooling months from April to September. We consider an electric heating system of the heat pump type, with a production efficiency of 3.5 and an electric cooling system with an efficiency of 3. For more information, visit our online tool.

02 Advice based on glazed surface area up to 2.5 m², please contact us for any confirmation or thermal shock analysis.
The data in this information sheet is not contractual, SOLAR SCREEN reserves the right to modify the composition of its products at any time. Please refer to our warranties and general sales conditions.