



Solar  Screen

NEUTRAL 440 C

Safety
Security - Combination

Description

Neutral 440 C films are highly effective at reducing solar heat gain, whilst at the same time continuing to allow some natural light transmission. They help noticeably reduce solar glare, their tinted aspect helping convey a touch of colour and customization to the external aspect of a building. Designed to act as a security film, it provides protection by holding shattered glass in place in the event of an impact.

Certifications



REACH / RoHS
Compliant



EN 12600
2B2













Fire Resistance Rating
M1



View test videos on
the safety film

Characteristics



-  **Warranty**
5 years
-  **Fire Resistance Rating**
M1
-  **Storage in recommended conditions**
3 years
-  **REACH / RoHS**
Compliant
-  **EN 12600**
2B2
-  **Widths Available**
152 cm
-  **Installation Type**
Interior
-  **Color From the Outside**
Neutral
-  **Length**
30.5 m
-  **Product Carbon Footprint (LCA)**
2.2 kgCO₂e/m²

Construction

- Scratch-resistant hard coating providing surface protection, durability, and ease of cleaning
- High optical quality polyester
- Bonding adhesive
- High optical quality polyester
- Reinforced PS adhesive to accompany the elasticity of the film in case of impact, polymerizes with glass within 30 days
- Protection PET release liner, disposable after installation

-  **Composition**
PET
-  **Thickness**
125 µm

Mechanical Properties

-  **Tensile strength at break**
220 MPa
-  **Elongation at break**
125%

Optical and solar properties

Pane type	Single 3mm		Double Low-E	
	No film	With Film	No film	With Film
UV Rejection (%)	25	99	40	99
Visible Light Transmission (%)	91	63	82	57
Visible Light Reflection - External (%)	8	11	11	16
Visible Light Reflection - Internal (%)	8	10	12	16
Solar Energy Reflection (%)	5	7	12	23
Solar Energy Absorption (%)	8	31	28	35
Solar Energy Transmission (%)	87	62	60	42
Total Solar Energy Rejected (%)	12	37	35	40
Glare Reduction (%)	-	38	-	31
Shading Coefficient	-	0.80	-	1.0
g-value	0.88	0.70	0.65	0.65
U-value (W/m ² .°C)	5.8	5.8	1.1	1.1

Application advice⁰¹

Vertical situation and for a standard glazed surface

Clear Single Pane	✓
Tinted Single Pane	!
Reflective Tinted Single Pane	✓
Clear Double Pane	✓
Tinted Double Pane	!
Reflective Tinted Double Pane	✓
Gas-Filled Double Pane - Low E	!
Stadip Ext. Clear Double Pane	!
Stadip Int. Clear Double Pane	✗

✓ Yes ✗ Not recommended ! Caution

Installation and Maintenance Advise

Safety film with reinforced PS adhesive, requiring a suitable application solution : Slide On (600-F02) or Film On (600-F0355) diluted at 2 cL/L of water, and a suitable safety squeegee (150-054 / 150-055 / 150-056). Do not clean for at least one month or apply stickers/adhesives to the film.



Download the
installation and
maintenance advice

⁰¹ Advice based on glazed surface area up to 2.5 m², please contact us for any confirmation or thermal shock analysis.
The data in this information sheet is not contractual, SOLAR SCREEN reserves the right to modify the composition of its products at any time. Please refer to our warranties and general sales conditions.