

Exterior

Interior

Solar Screen

VISTA 99 XC - Day/Night Discretion

Solar Control

One Way Mirror - Exterior

Description

Vista 99 XC Day/Night Discretion films effectively eliminate solar heat gain and solar glare, whilst still allowing vision through the glass towards the exterior. Its one-way mirror aspect guarantees privacy from prying eyes by creating a visual barrier practically during daylight hours and at night.

Visible Light Transmission (%)




Visible Light Reflection - External (%)



UV Rejection (%)












Total Solar Energy Rejected (%)



||| 3 mm simple glazing - without film ■ Film applied to 3 mm simple glazing



Characteristics

-  **Warranty**
3 years
-  **Fire Resistance Rating**
M1
-  **Storage in recommended conditions**
3 years
-  **REACH / RoHS**
Compliant
-  **Widths Available**
152 cm
-  **Installation Type**
Exterior
-  **Color From the Outside**
Silver
-  **Length**
30.5 m
-  **Product Carbon Footprint (LCA)**
1.49 kgCO2e/m²

Construction

- 1 Scratch-resistant hard coating providing surface protection, durability, and ease of cleaning
- 2 High optical quality polyester, with an IR-blocking metallic particle coating
- 3 Bonding adhesive
- 4 High optical quality dyed polyester
- 5 PS adhesive, polymerizes with glass within 15 days
- 6 Protection PET release liner, disposable after installation

-  **Composition**
PET
-  **Thickness**
75 µm

Details



Energy and environmental benefits⁰¹

 **Energy savings**
128.6 kWh/m²/year

 **Carbon footprint reduction**
40.6 kgCO₂/m²

 **Financial savings**
30 euros/m²/year



Access our energy savings calculator

Optical and solar properties

Pane type	Single 3mm		Double Low-E	
	No film	With Film	No film	With Film
UV Rejection (%)	25	99	40	99
Visible Light Transmission (%)	91	1	82	1
Visible Light Reflection - External (%)	8	88	11	88
Visible Light Reflection - Internal (%)	8	11	12	11
Solar Energy Reflection (%)	5	84	28	85
Solar Energy Absorption (%)	8	14	12	14
Solar Energy Transmission (%)	87	2	60	1
Total Solar Energy Rejected (%)	12	95	35	97
Infrared Rejection (780 - 2500 nm) (%)	16	97	16	98
Glare Reduction (%)	-	99	-	99
Shading Coefficient	-	0.06	-	0.03
g-value	0.88	0.07	0.65	0.03
U-value (W/m ² .°C)	5.8	5.8	1.1	1.1

Application advice⁰²

Vertical situation and for a standard glazed surface

- Clear Single Pane ✓
- Tinted Single Pane ✓
- Reflective Tinted Single Pane ✓
- Clear Double Pane ✓
- Tinted Double Pane ✓
- Reflective Tinted Double Pane ✓
- Gas-Filled Double Pane - Low E ✓
- Stadip Ext. Clear Double Pane ✓
- Stadip Int. Clear Double Pane ✓

✓ Yes ✗ Not recommended ! Caution

Installation and Maintenance Advise

Use Slide On (600-FO2) or Film On (600-F0355) diluted at 2 cL/L of water for installation and cleaning. Do not clean for one month after installation or apply stickers/adhesives on the film.



Access the installation and maintenance advice video

⁰¹ Values based on a study carried out on an air-conditioned building located in Luxembourg, with a film applied on a low-E double glazing, facing East. The heating months considered are from October to March, and the cooling months from April to September. We consider an electric heating system of the heat pump type, with a production efficiency of 3.5 and an electric cooling system with an efficiency of 3. For more information, visit our online tool.

⁰² Advice based on glazed surface area up to 2.5 m², please contact us for any confirmation or thermal shock analysis. The data in this information sheet is not contractual, SOLAR SCREEN reserves the right to modify the composition of its products at any time. Please refer to our warranties and general sales conditions.